

# Technical Data

## BARRIER



### Product description

Barrier is a two-pack zinc rich epoxy primer with a high content of zinc.

---

### Recommended use

As a primer on blast cleaned steel. Barrier is used in combination with advanced coating systems to further improve protection against corrosion.

---

### Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry (µm)	25	90	40
Film thickness, wet (µm)	45	170	75
Theoretical spreading rate (m <sup>2</sup> /l)	21,2	5	13,3

### Comments

In a systems of DFT of max. 90 µm, the drying time will increase.

---

### Physical properties

Colour	Grey
Solids (vol %)*	53 ± 2
Flash point	27°C ± 2 (Setaflash)
Gloss	Flat
Water resistance	Excellent
Abrasion resistance	Very good
Solvent resistance	Very good
Flexibility	Good
Compatibility with cathodic protection	Good

\*Measured according to ISO 3233:1998 (E)

---

### Surface preparation

All surfaces should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

#### Bare steel

Cleanliness: Blast cleaning to min. Sa 2 ½ (ISO 8501-1:1988) or for maintenance UHPWJ to WJ2 (NACE No.5/SSPC-SP 12). Roughness: using abrasives suitable to achieve grade Fine to Medium G (30-85 µm, Ry5) (ISO 8503-2)

#### Shopprimed steel

Clean, dry and undamaged approved shopprimer.

#### Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

---

## Condition during application

The temperature of the substrate should be minimum 5°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is required in confined areas to ensure correct drying.

---

## Application methods

**Spray** Use airless spray  
**Brush** Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.

---

## Application data

**Mixing ratio (volume)** 3 part Comp. A (base) to be mixed thoroughly with 1 part Comp. B (curing agent)  
**Mixing** ½ hour prior to use.  
**Pot life (23°C)** 24 hours. (Reduced at higher temp.).  
**Thinner/Cleaner** Jotun Thinner No. 17  
**Guiding data airless spray**  
**Pressure at nozzle** 15 MPa min (150 kp/cm<sup>2</sup>, 2100 psi.).  
**Nozzle tip** 0.38 - 0.53 mm (0.015 - 0.021").  
**Spray angle** 40 - 80°  
**Filter** Check to ensure that filters are clean.

---

## Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- \* Good ventilation (Outdoor exposure or free circulation of air)
- \* Typical film thickness
- \* One coat on top of inert substrate

Substrate temperature	5°C	10°C	23°C	40°C
Surface dry	50 min	20 min	10 min	4 min
Through dry	3 h	2 h	1,5 h	0,7 h
Cured	10 d	7 d	5 d	2 d
Dry to recoat, minimum <sup>1</sup>	3 h	2 h	1,5 h	0,7 h
Dry to recoat, maximum <sup>1,2</sup>				

1. Recommended data given for recoating with coatings normally specified on top of zinc epoxy coatings.
2. The surface should be dry and free from any contamination prior to application of the subsequent coat.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

---

## Typical paint system

**Barrier** **1 x 25 - 90 µm** **(Dry Film Thickness)**

Subsequent coating(s) by choice e.g.: epoxy, acrylic or vinyl.

**Other systems may be specified, depending on area of use**

---

## Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

---

## Handling

Handle with care. Stir well before use. Continuous stirring during application will prevent the heavy zinc pigment from settling.

---

## Packing size

4 litre unit: 3 litres Comp. A (base) in a 5 litre container and 1 litre Comp. B (curing agent) in a 1 litre container.

or

9 litre unit: 6.75 litres Comp. A (base) in a 10 litre container and 2.25 l Comp. B (curing agent) in a 3 litre container.

Packing may vary from country to country according to local requirements.

---

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

**For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.**

---

### DISCLAIMER

*The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.*

#### Head Office & Nordic

Jotun Paints  
P.O. Box 2021  
N-3248 Sandefjord  
Norway  
Phone +47 33 45 70 00  
Fax +47 33 46 46 13

#### Europe

Jotun Paints (Europe) Ltd.  
Stather Road, Flixborough  
North Lincolnshire DN15 8RR  
United Kingdom  
Phone +44 172 44 00 000  
Fax +44 172 44 00 100

#### Middle East

Jotun U.A.E Ltd. LLC.  
Al Quoz Industrial Area  
P.O Box 3671  
Dubai U.A.E  
Phone +971 4 3 39 50 00  
Fax +971 4 3 38 06 66

#### South East Asia

Jotun (Singapore) Pte. Ltd.  
No 11-15, Sixth Lok Yang Road  
Jurong  
Singapore 628 111  
Phone +65 6265 4711  
Fax +65 6265 7484

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at [www.jotun.com](http://www.jotun.com)

ISSUED 16 MAY 2003 BY JOTUN PAINTS  
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED

---

PDF Version :

