

Technical Data

Penguard Special



Product description

Penguard Special is a high build, two-pack zinc phosphate pigmented epoxy coating based on epoxy resin with high molecular weight.

Recommended use

As an anti corrosive primer and intermediate coating for corrosion protection of various substrates including steel.

Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry (μm)	40	150	100
Film thickness, wet (μm)	80	300	200
Theoretical spreading rate (m^2/l)	12,6	3,3	5

Comments

For DFTs below 80 μm thinner should be used

Approvals

1. APAS approved to specification 2971.
 2. Approved to UNE 48271.
-

Physical properties

Colour	Grey, Red, White
Solids (vol %)*	50 \pm 2
Flash point	25°C \pm 2 (Setaflash)
VOC	390 gms/ltr UK-PG6/23(97). Appendix 3
Gloss	Flat
Water resistance	Very good
Abrasion resistance	Very good
Solvent resistance	Excellent
Chemical resistance	Excellent
Flexibility	Good

*Measured according to ISO 3233:1998 (E)

Surface preparation

All surfaces should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

Bare steel

Cleanliness: Blast cleaning to Sa 2½ (ISO 8501-1:2007). Roughness: using abrasives suitable to achieve grade Fine to Medium G (30-85 µm, Ry5) (ISO 8503-2)

Shopprimed steel

Clean, dry and undamaged approved shopprimer.

Coated surfaces

Clean, dry and undamaged compatible primer. Contact your local Jotun office for more information.

Other surfaces

For aluminium and galvanized surface; degreasing, light abrading or sand sweeping.

The coating may be used on other substrates. Please contact your local Jotun office for more information.

Condition during application

The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying. The coating should not be exposed to oil, chemicals or mechanical stress until cured. If necessary, Penguard Stayer, Penguard Primer, Penguard HB, Penguard Special may be used down to 2°C, provided a special accelerator is added.

Application methods

Spray	Use airless spray
Brush	Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.

Application data

Mixing ratio (volume)	4:1
Mixing	4 parts Comp. A (base) to be mixed thoroughly with 1 part Penguard, Comp. B (curing agent).
Induction time	30 minutes.
Pot life (23°C)	8 hours. (Reduced at higher temp.)
Thinner/Cleaner	Jotun Thinner No. 17
Guiding data airless spray	
Pressure at nozzle	15 MPa (150 kp/cm ² , 2100 psi)
Nozzle tip	0.46-0.69 mm (0.018-0.027")
Spray angle	40-80°
Filter	Check to ensure that filters are clean.

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- * Good ventilation (Outdoor exposure or free circulation of air)
- * Typical film thickness
- * One coat on top of inert substrate

Normal hardener			
Substrate temperature	10°C	23°C	40°C
Surface dry	4 h	2 h	1 h
Through dry	16 h	8 h	3 h
Cured	14 d	7 d	3 d
Dry to recoat, minimum	16 h	8 h	3 h
Dry to recoat, maximum ¹			

1. Provided the surface is free from chalking and other contamination prior to application, there is normally no overcoating time limit. If the coating has been exposed to direct sunlight for some time, special attention must be paid to surface cleaning and mattening/removal of the surface layer in order to obtain good adhesion.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Typical paint system

Penguard Special **1 - 2 x 100 µm** **(Dry Film Thickness)**
 Normally topcoated with Epoxy or Polyurethane.

Other systems may be specified, depending on area of use

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing size

20 litre unit: 16 litres Comp. A (base) in a 20 litre container and 4 litres Penguard, Comp. B (curing agent) in a 5 litre container

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED 19 MARCH 2009 BY JOTUN
 THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED